

ANHUI SINOGRACE CHEMICAL

Primid polyester resin for powder coating

Type	Acid value (mgKOH/g)	Viscosity (mpa.s, 200 °C)	Tg (°C)	Curing (°C/min)	Features	Note
SG9011	28~32	3500~6000	≥61	180/10~15	95/5, general purpose, good leveling and mechanical properties	
SG9012	28~32	3500~5500	≥59	180/15	95/5, good leveling, high gloss, excellent boiling water resistance and weatherability	
SG9015	24~27	4500~6500	≥57	180/10~15	96/4, good leveling, anti yellowing and good weatherability	
SG9122	28~32	3000~5000	≥56	180/10~15	95/5, high leveling, high gloss, excellent thick coating and weatherability	
SG9588	28~32	6000~8000	≥60	180/15	95/5, super weatherability resin	
SG9700	29~33	3000~6000	≥53	160/15	95/5, low temperature curing resin, good mechanical property and weatherability	
SG9800	19~25	6000~8500	≥55	180/10	96.5/3.5, low Primid dosage, good mechanical property and weatherability	
SG9811	19~24	5500~8500	≥61	180/15 200/10	96.5/3.5, high Tg, good mechanical property and weatherability. Matting while mixed with SG9866	
SG9855	28~32	4500~6500	≥57	180/15	95/5, high temperature resistance, good mechanical properties and weatherability	Baking resistance
SG9866	48~53	6500~8500	≥60	180/15	93/7, high acid value resin, high Tg. Matting while mixed with SG9811	

CONTACT US

Jack Tao

Export Director

Mob:+86-15855525589

Email: sales@sinogracechem.com

Anhui Sinograce Chemical Co., Ltd.

**Add: Suite 1116-1117, Block C, Feixi Road, Shushan District, Hefei city, Anhui province,
China**

Tel:+86-551-63459511/Fax:+86-551-63668835

Web: www.sinogracechem.com