

ANHUI SINOGRACE CHEMICAL

70/30 Hybrid polyester resin for powder coating

Type	Acid value (mgKOH/g)	Viscosity (mpa.s, 200 °C)	Tg (°C)	Curing (°C/min)	Features	Note
SG7011	32~38	2500~5000	≥54	180/15	Excellent bending resistance and impact resistance	
SG7012	32~36	4000~7000	≥51	180/15	Used for matte powder coating, good leveling and mechanical properties	
SG7511	32~36	3000~5500	≥52	180/15	Good boiling water resistance, anti-freezing and good mechanical properties	
SG7700	32~38	3000~6000	≥53	160/15	Low curing temperature, good mechanical and bending resistance properties	
SG7701	28~38	4000~6000	≥57	180/10	Fast curing resin, good leveling and stability	
SG7800	30~35	5000~8000	≥61	180/15	High Tg, excellent mechanical properties and stability	

CONTACT US

Jack Tao

Export Director

Mob:+86-15855525589

Email: sales@sinogracechem.com

Anhui Sinograce Chemical Co., Ltd.

Add: Suite 1116-1117, Block C, Feixi Road, Shushan District, Hefei city, Anhui province, China

Tel:+86-551-63459511/Fax:+86-551-63668835

Web: www.sinogracechem.com