METAL SURFACE TEATMENT



Degreaser and rust remover for metal MC-DE6810B

- Non corrosion effect on the metal surface
- One-time processing complete to degrease and remove rust

FEATURE

- No acid mist, no pollution, low foaming and acid liquid products
- Can effectively remove cold rolled steel, cast iron and precision parts surface grease, rust, dust and dirt.
- Appearance: Colorless or yellowish liquid
- Applied temperature: Normal temperature~70°C
- MC-DE6810B applied concentration: 100%
- Treatment time: 5~20min
- pH: ≤1.5
- Treatment way: Dip or spray

Add the MC-DE6810B 1000L into a tank. Then using treat the metal by dipping or spraying. Please remove rust, dust oil and other pollution by overflow or other way in time. It need to supplement the MC-DE6810B, when the effect can not meet your request.

APPLICATION

PROCESS

Free acidity test method: Firstly, add 10ml aqueous into an Erlenmeyer flask. Then add 0.1~0.5ml bromophenol blue indicator. Using 0.1mol/L NaOH standard solution to titrate it. While the solution changes from yellow to light blue. The consumption volume of 0.1mol/L NaOH standard solution is the free acidity value.

Total acidity test method: Firstly, add 10ml aqueous into an Erlenmeyer flask. Then add 0.1~0.5ml phenolphthalein indicator. Using 0.1mol/L NaOH standard solution to titrate it. While the solution changes from colorless to light red. The consumption volume of 0.1mol/L NaOH standard solution is the total acidity value.

APPLICATION

- Cold rolled steel, cast iron
- Metal precision part etc.

• Please wear the protective gloves when using it.

• MC-DE6810B is acid liquid and wear the protective equipment while using it.

NOTE

- It contains the phosphate and please treat the waste liquid before discharge.
- Wash immediately with water when skin encounter the cleaning agent.

Anhui Sinograce Chemical Co., Ltd. Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589

METAL SURFACE TEATMENT



STORAGE AND HANDLING

- Available in 200 kg/ barrel or 25 kg/ barrel
- Storage period: ~12 months in closed containers, shady and dry place

Anhui Sinograce Chemical Co., Ltd. Add.: Hefei city, Anhui province, China Tel: +86-0551-63459511 Mob: +86 15855525589

Email: sales@sinogracechem.com